

Primary material: TangoBlackPlus FLX980 / TangoPlus FLX930

Secondary material: VeroWhitePlus RGD835

Property	ASTM	Units	FLX9840-DM FLX9740-DM	FLX9850-DM FLX9750-DM	FLX9860-DM FLX9760-DM	FLX9870-DM FLX9770-DM	FLX9885-DM FLX9785-DM	FLX9895-DM FLX9795-DM
Tensile strength	D-412	MPa	0.5-1.5	0.5-1.5	2-4	2-4	4-8.	15-25
Elongation at break	D-412	%	150-170	130-150	80-100	50-70	50-60	25-35
Shore Hardness (A)	D-2240	Scale A	35-45	45-55	55-65	65-75	80-90	90-100
Tensile Tear resistance	D-624	Kg/cm	4-6	5-7	7-9	12-14	25-27	45-47